



SUPER-GUARD™ SYNTHETIC ROOFING UNDERLAYMENT
 Meets ASTM D226 and ASTM D4869. Florida Building Code Approved FL22409

BENEFITS

S-GUARD™ now with **TRUE GRIT Technology™**.

Utilizing a patent pending process **TRUE GRIT technology™** provides drastically improved skid resistance. Its sandpaper like effect provides much stronger friction points under typical roofing footwear, adding traction during installation.

- No tears - Much stronger than 30# asphalt felt
- Light - Easier to handle and carry than felt
 10 Sq. **S-GUARD™** weighs 22 lb
 2 Sq. 30# asphalt felt weighs 42 lb
- 90 Day UV exposure
- No asphalt - will not rot, dry-out, nor support mold growth
- No buckling, warping or cracking
- Dependable long term moisture protection for the roof
- Lays flat for quick and easy install
- Less laps - 48" wide **S-GUARD™** vs. 36" asphalt felt
- Cool blue color to reduce heat absorption on install
- 25 Year limited warranty
- 100% Recyclable - Considered a green building product

SPECIFICATIONS

ROLL SIZE	10 SQUARES	4 SQUARES
Surface Covered	1000 ft² (92.9 m²)	400 ft² (37.2 m²)
Length	250 ft (76.2 m)	100 ft (30.5 m)
Width	48" (1219 mm)	48" (1219 mm)
Rolls per Pallet	56	120
Weight per Roll	22 lbs	9 lbs

PROPERTIES	TEST METHOD	S-GUARD
Breaking Strength (lbf/in-width)	ASTM D 226	64 Longitudinal (with fiber grain)
	ASTM D 226	66 Transverse (across fiber grain)
Tear Resistance; min; (lbf)	ASTM D 4073	77 MD Longitudinal (with fiber grain)
	ASTM D 4073	76 CMD Transverse (across fiber grain)
Pliability	ASTM D 228	Pass - Longitudinal / Transverse
Behavior (loss) on Heating	ASTM D 228	- 0.0
Liquid Water Transmission [Pass/Fail]	ASTM D 4869	Pass
Dimensional Stability (%)	ASTM D 1204	2.5 Longitudinal (with fiber grain)
	ASTM D 1204	2.5 Transverse (across fiber grain)
Unrolling @ 30°F and 140°F; [Pass/Fail]	N/A	Pass
Nominal Thickness	ASTM D1777	6 mils

www.super-guard.ca | 416-299-1675 | info@acp99.com

Proudly made in North America
 by Atlantic Coated Papers